

# Technical data sheet



## AT-HP High Performance Resin

*AT-HP is a styrene free methacrylate resin suitable for high performance fixing applications in threaded rod into concrete.*

- *Easy to dispense and fast curing, it's specially designed for structural fixings and construction uses.*
- *ETA Option 8 for threaded rod and rebar*

## Features

### Material

- Styrene free methacrylate resin.
- Threaded rod: galvanised steel and stainless steel A4-70.

### Benefits

- Fast curing.
- Low odour.
- Non-flammable.
- Easy to dispense.

## Applications

### Header member

- Non-cracked concrete.
- Solid blocks.
- Hollow blocks.
- AAC Blocks.

### For Use With

- Threaded rod and rebar connections.
- Racking.
- Balconies.
- Facades.



Hollow block.



Post to concrete.

AT-HP  
High Performance Resin

## Technical Data

### Références

References	Product information						
	DB nr.	NOBB nr.	Grey color	Beige color	Content [ml]	Weight [kg]	Packaging qty [pcs]
ATHP300G-FR	-	-	x	-	300	0.575	12
ATHP420G-FR	-	-	x	-	420	0.828	12
ATHP300BG-DK	2099761	56432785	-	-	300	0.575	12

Design resistance – Tension – NRd [kN] – hef = 8d – Carbon steel 5.8

References	Design resistance – hef = 8d – Carbon steel 5.8							
	Tension - NRd [kN]							
	Cracked concrete				Non-cracked concrete			
	C20/25	C30/37	C40/50	C50/60	C20/25	C30/37	C40/50	C50/60
AT-HP + LMAS M8	-	-	-	-	10.7	12	12	12
AT-HP + LMAS M10	-	-	-	-	15.9	17.8	19.3	19.3
AT-HP + LMAS M12	8.4	8.8	9	9.2	21.7	24.3	26.7	28
AT-HP + LMAS M16	15	15.6	16.1	16.4	34.3	38.4	42.2	44.6
AT-HP + LMAS M20	-	-	-	-	50.2	56.3	61.8	65.3
AT-HP + LMAS M24	-	-	-	-	67.5	75.6	83.1	87.8

#### Concrete :

- The design loads have been calculated using the partial safety factors for resistances stated in ETA-approval(s). The loading figures are valid for unreinforced concrete and reinforced concrete with a rebar spacing  $s \geq 15$  cm (any diameter) or with a rebar spacing  $s \geq 10$  cm, if the rebar diameter is 10mm or smaller.
- The figures for shear are based on a single anchor without influence of concrete edges. For anchorages close to edges ( $c \leq \max [10 \text{ hef}; 60d]$ ) the concrete edge failure shall be checked per ETAG 001, Annex C, design method A.
- Concrete is considered non-cracked when the tensile stress within the concrete is  $\sigma_L + \sigma_R \leq 0$ . In the absence of detailed verification  $\sigma_R = 3 \text{ N/mm}^2$  can be assumed ( $\sigma_L$  equals the tensile stress within the concrete induced by external loads, anchors loads included).

## AT-HP High Performance Resin

Design resistance – Tension – NRd [kN] – hef = 12d – Carbon steel 5.8

References	Design resistance – hef = 12d – Carbon steel 5.8							
	Tension - NRd [kN]							
	Cracked concrete				Non-cracked concrete			
	C20/25	C30/37	C40/50	C50/60	C20/25	C30/37	C40/50	C50/60
AT-HP + LMAS M8	-	-	-	-	12	12	12	12
AT-HP + LMAS M10	-	-	-	-	19.3	19.3	19.3	19.3
AT-HP + LMAS M12	12.7	13.2	13.5	13.8	28	28	28	28
AT-HP + LMAS M16	22.5	23.4	24.1	24.5	51.4	52.7	52.7	52.7
AT-HP + LMAS M20	-	-	-	-	75.4	82	82	82
AT-HP + LMAS M24	-	-	-	-	101.3	113.4	118	118

### Concrete :

1. The design loads have been calculated using the partial safety factors for resistances stated in ETA-approval(s). The loading figures are valid for unreinforced concrete and reinforced concrete with a rebar spacing  $s \geq 15$  cm (any diameter) or with a rebar spacing  $s \geq 10$  cm, if the rebar diameter is 10mm or smaller.
2. The figures for shear are based on a single anchor without influence of concrete edges. For anchorages close to edges ( $c \leq \max [10 \text{ hef}; 60d]$ ) the concrete edge failure shall be checked per ETAG 001, Annex C, design method A.
3. Concrete is considered non-cracked when the tensile stress within the concrete is  $\sigma_L + \sigma_R \leq 0$ . In the absence of detailed verification  $\sigma_R = 3 \text{ N/mm}^2$  can be assumed ( $\sigma_L$  equals the tensile stress within the concrete induced by external loads, anchors loads included).

Design resistance – Tension – NRd [kN] – hef = 8d – Stainless steel A4-70

References	Design resistance – hef = 8d – Stainless steel A4-70							
	Tension - NRd [kN]							
	Cracked concrete				Non-cracked concrete			
	C20/25	C30/37	C40/50	C50/60	C20/25	C30/37	C40/50	C50/60
AT-HP + LMAS M8	-	-	-	-	10.7	12	13.2	13.9
AT-HP + LMAS M10	-	-	-	-	15.9	17.8	19.6	20.7
AT-HP + LMAS M12	8.4	8.8	9	9.2	21.7	24.3	26.7	28.2
AT-HP + LMAS M16	15	15.6	16.1	16.4	34.3	38.4	42.2	44.6
AT-HP + LMAS M20	-	-	-	-	50.2	56.3	61.8	65.3
AT-HP + LMAS M24	-	-	-	-	67.5	75.6	83.1	87.8

### Concrete :

1. The design loads have been calculated using the partial safety factors for resistances stated in ETA-approval(s). The loading figures are valid for unreinforced concrete and reinforced concrete with a rebar spacing  $s \geq 15$  cm (any diameter) or with a rebar spacing  $s \geq 10$  cm, if the rebar diameter is 10mm or smaller.
2. The figures for shear are based on a single anchor without influence of concrete edges. For anchorages close to edges ( $c \leq \max [10 \text{ hef}; 60d]$ ) the concrete edge failure shall be checked per ETAG 001, Annex C, design method A.
3. Concrete is considered non-cracked when the tensile stress within the concrete is  $\sigma_L + \sigma_R \leq 0$ . In the absence of detailed verification  $\sigma_R = 3 \text{ N/mm}^2$  can be assumed ( $\sigma_L$  equals the tensile stress within the concrete induced by external loads, anchors loads included).

## AT-HP High Performance Resin

Design resistance – Tension – NRd [kN] – hef = 12d – Stainless steel A4-70

References	Design resistance – hef = 12d – Stainless steel A4-70							
	Tension - NRd [kN]							
	Cracked concrete				Non-cracked concrete			
	C20/25	C30/37	C40/50	C50/60	C20/25	C30/37	C40/50	C50/60
AT-HP + LMAS M8	-	-	-	-	13.9	13.9	13.9	13.9
AT-HP + LMAS M10	-	-	-	-	21.9	21.9	21.9	21.9
AT-HP + LMAS M12	12.7	13.2	13.5	13.8	31.6	31.6	31.6	31.6
AT-HP + LMAS M16	22.5	23.4	24.1	24.5	51.4	57.6	58.8	58.8
AT-HP + LMAS M20	-	-	-	-	75.4	84.4	92	92
AT-HP + LMAS M24	-	-	-	-	101.3	113.4	124.6	131.7

### Concrete :

1. The design loads have been calculated using the partial safety factors for resistances stated in ETA-approval(s). The loading figures are valid for unreinforced concrete and reinforced concrete with a rebar spacing  $s \geq 15$  cm (any diameter) or with a rebar spacing  $s \geq 10$  cm, if the rebar diameter is 10mm or smaller.
2. The figures for shear are based on a single anchor without influence of concrete edges. For anchorages close to edges ( $c \leq \max [10 \text{ hef}; 60d]$ ) the concrete edge failure shall be checked per ETAG 001, Annex C, design method A.
3. Concrete is considered non-cracked when the tensile stress within the concrete is  $\sigma_L + \sigma_R \leq 0$ . In the absence of detailed verification  $\sigma_R = 3 \text{ N/mm}^2$  can be assumed ( $\sigma_L$  equals the tensile stress within the concrete induced by external loads, anchors loads included).

Design resistance – Shear – VRd [kN] – hef = 8d – Carbon steel 5.8

References	Design resistance – hef = 8d – Carbon steel 5.8							
	Shear - VRd [kN]							
	Cracked concrete				Non-cracked concrete			
	C20/25	C30/37	C40/50	C50/60	C20/25	C30/37	C40/50	C50/60
AT-HP + LMAS M8	-	-	-	-	7.2	7.2	7.2	7.2
AT-HP + LMAS M10	-	-	-	-	12	12	12	12
AT-HP + LMAS M12	16.8	16.8	16.8	16.8	16.8	16.8	16.8	16.8
AT-HP + LMAS M16	30	31.2	31.2	31.2	31.2	31.2	31.2	31.2
AT-HP + LMAS M20	-	-	-	-	48.8	48.8	48.8	48.8
AT-HP + LMAS M24	-	-	-	-	70.4	70.4	70.4	70.4

### Concrete :

1. The design loads have been calculated using the partial safety factors for resistances stated in ETA-approval(s). The loading figures are valid for unreinforced concrete and reinforced concrete with a rebar spacing  $s \geq 15$  cm (any diameter) or with a rebar spacing  $s \geq 10$  cm, if the rebar diameter is 10mm or smaller.
2. The figures for shear are based on a single anchor without influence of concrete edges. For anchorages close to edges ( $c \leq \max [10 \text{ hef}; 60d]$ ) the concrete edge failure shall be checked per ETAG 001, Annex C, design method A.
3. Concrete is considered non-cracked when the tensile stress within the concrete is  $\sigma_L + \sigma_R \leq 0$ . In the absence of detailed verification  $\sigma_R = 3 \text{ N/mm}^2$  can be assumed ( $\sigma_L$  equals the tensile stress within the concrete induced by external loads, anchors loads included).

## AT-HP High Performance Resin

Design resistance – Shear –  $V_{Rd}$  [kN] –  $h_{ef} = 12d$  – Carbon steel 5.8

References	Design resistance – $h_{ef} = 12d$ – Carbon steel 5.8							
	Shear - $V_{Rd}$ [kN]							
	Cracked concrete				Non-cracked concrete			
	C20/25	C30/37	C40/50	C50/60	C20/25	C30/37	C40/50	C50/60
AT-HP + LMAS M8	-	-	-	-	7.2	7.2	7.2	7.2
AT-HP + LMAS M10	-	-	-	-	12	12	12	12
AT-HP + LMAS M12	16.8	16.8	16.8	16.8	16.8	16.8	16.8	16.8
AT-HP + LMAS M16	31.2	31.2	31.2	31.2	31.2	31.2	31.2	31.2
AT-HP + LMAS M20	-	-	-	-	48.8	48.8	48.8	48.8
AT-HP + LMAS M24	-	-	-	-	70.4	70.4	70.4	70.4

### Concrete :

1. The design loads have been calculated using the partial safety factors for resistances stated in ETA-approval(s). The loading figures are valid for unreinforced concrete and reinforced concrete with a rebar spacing  $s \geq 15$  cm (any diameter) or with a rebar spacing  $s \geq 10$  cm, if the rebar diameter is 10mm or smaller.
2. The figures for shear are based on a single anchor without influence of concrete edges. For anchorages close to edges ( $c \leq \max [10 h_{ef}; 60d]$ ) the concrete edge failure shall be checked per ETAG 001, Annex C, design method A.
3. Concrete is considered non-cracked when the tensile stress within the concrete is  $\sigma_L + \sigma_R \leq 0$ . In the absence of detailed verification  $\sigma_R = 3$  N/mm<sup>2</sup> can be assumed ( $\sigma_L$  equals the tensile stress within the concrete induced by external loads, anchors loads included).

Design resistance – Shear –  $V_{Rd}$  [kN] –  $h_{ef} = 8d$  – Stainless steel A4-70

References	Design resistance – $h_{ef} = 8d$ – Stainless steel A4-70							
	Shear - $V_{Rd}$ [kN]							
	Cracked concrete				Non-cracked concrete			
	C20/25	C30/37	C40/50	C50/60	C20/25	C30/37	C40/50	C50/60
AT-HP + LMAS M8	-	-	-	-	8.3	8.3	8.3	8.3
AT-HP + LMAS M10	-	-	-	-	12.8	12.8	12.8	12.8
AT-HP + LMAS M12	16.9	17.6	18.1	18.4	19.2	19.2	19.2	19.2
AT-HP + LMAS M16	30	31.2	32.1	32.7	35.3	35.3	35.3	35.3
AT-HP + LMAS M20	-	-	-	-	55.1	55.1	55.1	55.1
AT-HP + LMAS M24	-	-	-	-	79.5	79.5	79.5	79.5

### Concrete :

1. The design loads have been calculated using the partial safety factors for resistances stated in ETA-approval(s). The loading figures are valid for unreinforced concrete and reinforced concrete with a rebar spacing  $s \geq 15$  cm (any diameter) or with a rebar spacing  $s \geq 10$  cm, if the rebar diameter is 10mm or smaller.
2. The figures for shear are based on a single anchor without influence of concrete edges. For anchorages close to edges ( $c \leq \max [10 h_{ef}; 60d]$ ) the concrete edge failure shall be checked per ETAG 001, Annex C, design method A.
3. Concrete is considered non-cracked when the tensile stress within the concrete is  $\sigma_L + \sigma_R \leq 0$ . In the absence of detailed verification  $\sigma_R = 3$  N/mm<sup>2</sup> can be assumed ( $\sigma_L$  equals the tensile stress within the concrete induced by external loads, anchors loads included).

## AT-HP High Performance Resin

Design resistance – Shear -  $V_{Rd}$  [kN] –  $h_{ef} = 12d$  – Stainless steel A4-70

References	Design resistance – $h_{ef} = 12d$ – Stainless steel A4-70							
	Shear - $V_{Rd}$ [kN]							
	Cracked concrete				Non-cracked concrete			
	C20/25	C30/37	C40/50	C50/60	C20/25	C30/37	C40/50	C50/60
AT-HP + LMAS M8	-	-	-	-	8.3	8.3	8.3	8.3
AT-HP + LMAS M10	-	-	-	-	12.8	12.8	12.8	12.8
AT-HP + LMAS M12	19.2	19.2	19.2	19.2	19.2	19.2	19.2	19.2
AT-HP + LMAS M16	35.3	35.3	35.3	35.3	35.3	35.3	35.3	35.3
AT-HP + LMAS M20	-	-	-	-	55.1	55.1	55.1	55.1
AT-HP + LMAS M24	-	-	-	-	79.5	79.5	79.5	79.5

### Concrete :

- The design loads have been calculated using the partial safety factors for resistances stated in ETA-approval(s). The loading figures are valid for unreinforced concrete and reinforced concrete with a rebar spacing  $s \geq 15$  cm (any diameter) or with a rebar spacing  $s \geq 10$  cm, if the rebar diameter is 10mm or smaller.
- The figures for shear are based on a single anchor without influence of concrete edges. For anchorages close to edges ( $c \leq \max [10 h_{ef}; 60d]$ ) the concrete edge failure shall be checked per ETAG 001, Annex C, design method A.
- Concrete is considered non-cracked when the tensile stress within the concrete is  $\sigma_L + \sigma_R \leq 0$ . In the absence of detailed verification  $\sigma_R = 3$  N/mm<sup>2</sup> can be assumed ( $\sigma_L$  equals the tensile stress within the concrete induced by external loads, anchors loads included).

Design resistance – Bending moment –  $M_{Rd}$  [Nm] – Concrete

References	Design resistance – Bending moment – $M_{Rd}$ [Nm]	
	Carbon steel 5.8	Stainless steel A4-70
AT-HP + LMAS M8	15.2	16.7
AT-HP + LMAS M10	29.6	34
AT-HP + LMAS M12	52.8	59
AT-HP + LMAS M16	133.6	149.4
AT-HP + LMAS M20	260.8	291
AT-HP + LMAS M24	448.8	502.6

### Concrete :

- The design loads have been calculated using the partial safety factors for resistances stated in ETA-approval(s). The loading figures are valid for unreinforced concrete and reinforced concrete with a rebar spacing  $s \geq 15$  cm (any diameter) or with a rebar spacing  $s \geq 10$  cm, if the rebar diameter is 10mm or smaller.
- The figures for shear are based on a single anchor without influence of concrete edges. For anchorages close to edges ( $c \leq \max [10 h_{ef}; 60d]$ ) the concrete edge failure shall be checked per ETAG 001, Annex C, design method A.
- Concrete is considered non-cracked when the tensile stress within the concrete is  $\sigma_L + \sigma_R \leq 0$ . In the absence of detailed verification  $\sigma_R = 3$  N/mm<sup>2</sup> can be assumed ( $\sigma_L$  equals the tensile stress within the concrete induced by external loads, anchors loads included).

## AT-HP High Performance Resin

Design resistance – Tension –  $N_{Rd}$  [kN] – Rebar

References	Design resistance – $N_{Rd}$ – Carbon steel 5.8 [kN]							
	Non-cracked concrete							
	$h_{ef} = 8d$				$h_{ef} = 12d$			
	C20/25	C30/37	C40/50	C50/60	C20/25	C30/37	C40/50	C50/60
AT-HP + Ø8	6.3	7	7.7	8.1	9.4	10.5	11.5	12.2
AT-HP + Ø10	10.5	11.7	12.9	13.6	15.7	17.6	19.3	20.4
AT-HP + Ø12	14.1	15.8	17.3	18.3	21.1	23.6	26	27.4
AT-HP + Ø14	19.1	21.4	23.6	24.9	28.7	32.2	35.3	37.3
AT-HP + Ø16	23.2	26	28.6	34.8	34.8	39	42.8	52.2
AT-HP + Ø20	36.3	40.6	44.6	47.2	54.4	61	66.9	70.8
AT-HP + Ø25	52.3	58.6	64.4	68	78.5	87.9	96.6	102.1

Design resistance – Shear –  $V_{Rd}$  [kN] – Rebar

References	Design resistance – $V_{Rd}$ – Carbon steel 5.8 [kN]							
	Non-cracked concrete							
	$h_{ef} = 8d$				$h_{ef} = 12d$			
	C20/25	C30/37	C40/50	C50/60	C20/25	C30/37	C40/50	C50/60
AT-HP + Ø8	9.3	9.3	9.3	9.3	9.3	9.3	9.3	9.3
AT-HP + Ø10	14.7	14.7	14.7	14.7	14.7	14.7	14.7	14.7
AT-HP + Ø12	20.7	20.7	20.7	20.7	20.7	20.7	20.7	20.7
AT-HP + Ø14	28	28	28	28	28	28	28	28
AT-HP + Ø16	36.7	36.7	36.7	36.7	36.7	36.7	36.7	36.7
AT-HP + Ø20	57.3	57.3	57.3	57.3	57.3	57.3	57.3	57.3
AT-HP + Ø25	90	90	90	90	90	90	90	90

Design resistance – Bending moment –  $M_{Rd}$  [Nm] – Rebar

References	Design resistance – Bending moment – $M_{Rd}$ [Nm]
AT-HP + Ø8	22
AT-HP + Ø10	43.3
AT-HP + Ø12	74.7
AT-HP + Ø14	118.7
AT-HP + Ø16	176.7
AT-HP + Ø20	345.3
AT-HP + Ø25	674.7

AT-HP  
High Performance Resin

## Installation

### Curing Schedule

Temperature of the anchorage base $T_{\text{base material}}$	Working time (Gel time) $t_{\text{gel}}$	Curing time (in dry concrete) $t_{\text{cure, dry}}$	Curing time (in wet concrete) $t_{\text{cure, wet}}$
$0^{\circ}\text{C} \leq T_{\text{base material}} < +5^{\circ}\text{C}$	25 min	90 min	3:00 h
$5^{\circ}\text{C} \leq T_{\text{base material}} < +10^{\circ}\text{C}$	17 min	70 min	2:20 h
$10^{\circ}\text{C} \leq T_{\text{base material}} < +20^{\circ}\text{C}$	12 min	65 min	2:10 h
$20^{\circ}\text{C} \leq T_{\text{base material}} < +30^{\circ}\text{C}$	6 min	60 min	2:00 h
$30^{\circ}\text{C} \leq T_{\text{base material}} \leq +40^{\circ}\text{C}$	3 min	45 min	1:30 h

- **Manual Air Cleaning (MAC)** for all drill hole diameters  $d_0 \leq 24$  mm and drill holl depth  $h_0 \leq 10d$  :  
 4x blowing (hand pump)  
 4x brushing  
 4x blowing (Hand pump)
- **Compressed Air Cleaning (CAC)** for all drill hole diameters  $d_0$  and drill hole depths :  
 2x blowing (min. 6 bar - oil free compressed air)  
 2x brushing  
 2x blowing (min. 6 bar - oil free compressed air)
- **Cartridge temperature (Bond material) :  $\geq +20^{\circ}\text{C}$**

### Drilling methods


Solid brick/concrete	Percussion/hammer drilling
Hollow/perforated brick	Rotation drilling
Aerated concrete	Percussion/hammer drilling



## AT-HP High Performance Resin



*Drill.*




*Brush.*



*Insert sieve.*



*Inject the resin.*




*Insert the rod, turning slowly.*



*Once set, full load capacity is reached.*



*Drill.*



*Remove dust by brushing and blowing.*



*Fill the hole to half or two thirds. Withdrawing the nozzles with each pump.*



*Insert the rod, turning slowly.*



*Once set, full load capacity is reached.*

### Installation parameters – Concrete

References	Installation parameters - Concrete					
	Ø drilling [d <sub>0</sub> ] [mm]	Max. fixture hole Ø [d <sub>f</sub> ] [mm]	Drilling depth (8d) [h <sub>0</sub> =h <sub>ef</sub> =8d] [mm]	Drilling depth (12d) [h <sub>0</sub> =h <sub>ef</sub> =12d] [mm]	Wrench size [SW]	Installation torque [T <sub>inst</sub> ] [Nm]
AT-HP + LMAS M8	10	9	64	96	13	10
AT-HP + LMAS M10	12	12	80	120	17	20
AT-HP + LMAS M12	14	14	96	144	19	30
AT-HP + LMAS M16	18	18	128	192	24	60
AT-HP + LMAS M20	24	22	160	240	30	90
AT-HP + LMAS M24	28	26	192	288	36	140

## AT-HP High Performance Resin

### Spacing, edge distances and member thickness - Concrete

References	Spacing, edge distance and member thickness - Concrete									
	Effective embedment depth (8d) [h <sub>ef,8d</sub> ] [mm]	Characteristic spacing for h <sub>ef,8d</sub> [S <sub>cr,N</sub> ] [mm]	Characteristic edge distance for h <sub>ef,8d</sub> [C <sub>cr,N</sub> ] [mm]	Min. member thickness for h <sub>ef,8d</sub> [h <sub>min</sub> ] [mm]	Effective embedment depth (12d) [h <sub>ef,12d</sub> ] [mm]	Characteristic spacing for h <sub>ef,12d</sub> [S <sub>cr,N</sub> ] [mm]	Characteristic edge distance for h <sub>ef,12d</sub> [C <sub>cr,N</sub> ] [mm]	Min. member thickness for h <sub>ef,12d</sub> [h <sub>min</sub> ] [mm]	Min. spacing [S <sub>min</sub> ] [mm]	Min. edge distance [C <sub>min</sub> ] [mm]
AT-HP + LMAS M8	64	192	96	100	96	288	144	100	40	40
AT-HP + LMAS M10	80	240	120	110	120	360	180	150	50	50
AT-HP + LMAS M12	96	288	144	126	144	432	216	174	60	60
AT-HP + LMAS M16	128	384	192	158	192	576	288	222	80	80
AT-HP + LMAS M20	160	480	240	190	240	720	360	270	100	100
AT-HP + LMAS M24	192	576	288	222	288	864	432	318	120	120

### Installation parameters – Rebar

References	Installation parameters - Rebar		
	Ø drilling [d <sub>l</sub> ] [mm]	Drilling depth (8d) [h <sub>0</sub> =h <sub>ef</sub> =8d] [mm]	Drilling depth (12d) [h <sub>0</sub> =h <sub>ef</sub> =12d] [mm]
AT-HP + Ø8	12	64	96
AT-HP + Ø10	14	80	120
AT-HP + Ø12	16	96	144
AT-HP + Ø14	18	112	168
AT-HP + Ø16	20	128	192
AT-HP + Ø20	25	160	240
AT-HP + Ø25	32	200	300

### Spacing, edge distances and member thickness – Rebar

References	Spacing, edge distance and member thickness - Rebar									
	Effective embedment depth (8d) [h <sub>ef,8d</sub> ] [mm]	Characteristic spacing for h <sub>ef,8d</sub> [S <sub>cr,N</sub> ] [mm]	Characteristic edge distance for h <sub>ef,8d</sub> [C <sub>cr,N</sub> ] [mm]	Min. member thickness for h <sub>ef,8d</sub> [h <sub>min</sub> ] [mm]	Effective embedment depth (12d) [h <sub>ef,12d</sub> ] [mm]	Characteristic spacing for h <sub>ef,12d</sub> [S <sub>cr,N</sub> ] [mm]	Characteristic edge distance for h <sub>ef,12d</sub> [C <sub>cr,N</sub> ] [mm]	Min. member thickness for h <sub>ef,12d</sub> [h <sub>min</sub> ] [mm]	Min. spacing [S <sub>min</sub> ] [mm]	Min. edge distance [C <sub>min</sub> ] [mm]
AT-HP + Ø8	64	192	96	100	96	288	144	100	40	40
AT-HP + Ø10	80	240	120	110	120	360	180	150	50	50
AT-HP + Ø12	96	288	144	126	144	432	216	174	60	60
AT-HP + Ø14	112	336	168	148	168	504	252	204	70	70
AT-HP + Ø16	128	384	192	168	192	576	288	232	80	80
AT-HP + Ø20	160	480	240	210	240	720	360	290	100	100
AT-HP + Ø25	200	600	300	264	300	900	450	364	125	125



AT-HP  
**High Performance Resin**

Winchester Road Cardinal Point Tamworth Staffordshire B78 3HG  
tel: +44 1827 255600  
fax: +44 1827 255616

AT-HP  
**High Performance Resin**



Copyright by Simpson Strong-Tie®  
Information presented on this document is the exclusive property of Simpson Strong-Tie®  
It is valid only when associated with products supplied by Simpson Strong-Tie®

2024-04-21

[www.strongtie.co.uk](http://www.strongtie.co.uk)